

WHAT IS CLAIMED IS:

1. A conductive urethane composition comprising polyurethane obtained by a poly-addition reaction of polyol and polyisocyanate, wherein polyether polyol is used as said polyol;
5 and an average value of a non-saturation degree of said polyether polyol is set to not more than 0.025 milliequivalents/g.

2. The conductive urethane composition according to claim 1, having a compression set not more than 15% when said
10 compression set is measured at 70°C for 24 hours in a permanent set testing methods for rubber, vulcanized or thermoplastic specified in JIS K6262; a volume resistivity less than $10^{9.0}$ ($\Omega \cdot \text{cm}$) when said volume resistivity is measured at an applied voltage of 500V in a method specified in JIS K6911; and a
15 hardness not more than 55 degrees when said hardness is measured in accordance with a durometer hardness test type A specified in JIS K-6253.

3. The conductive urethane composition according to claim 1, containing an organic ionic-conductive agent other than
20 ammonium salts containing chlorine or bromine to set said volume resistivity of said conductive urethane composition to not more than $10^{8.0}$ ($\Omega \cdot \text{cm}$).

4. The conductive urethane composition according to claim 3, wherein organometallic salts having fluoro groups and/or
25 sulfonyl groups is contained as said organic ionic-conductive

agent.

5. The conductive urethane composition according to claim 4, wherein metal salts of bis(fluoroalkyl-sulfonyl)imide and/or metal salts of fluoroalkyl sulfonic acid is contained as said organometallic salts having said fluoro groups and/or said sulfonyl groups.

6. The conductive urethane composition according to claim 4, wherein not less than 0.5% of said organometallic salt is single-ionized.

10 7. The conductive urethane composition according to claim 1, wherein said polyether polyol contains ethylene oxide and/or propylene oxide at not less than 50 wt%.

8. The conductive urethane composition according to claim 1, wherein said polyether polyol has polypropylene glycol as a base thereof.

9. The conductive urethane composition according to claim 3, wherein not less than 0.01 parts by weight of said organic ionic-conductive agent nor more than 5.0 parts by weight thereof is used for 100 parts by weight of said polyol.

20 10. A conductive roller manufactured by preparing a cylindrical body composed of the conductive urethane composition according to claim 1 and by mounting a metal shaft on said cylindrical body.

11. The conductive roller according to claim 10, wherein a peripheral surface of said metal shaft is treated with plasma,

and said peripheral surface of said metal shaft and an inner peripheral surface of said cylindrical body are bonded to each other.

12. The conductive roller, according to claim 10, that is
5 used as a charging roller for uniformly charging a photosensitive drum of an electrophotographic apparatus.

13. The conductive roller, according to claim 10, that is used as a developing roller for attaching toner to a photosensitive member of an electrophotographic apparatus.

10 14. The conductive roller, according to claim 10, that is used as a transfer roller for transferring a toner image from a photosensitive member of an electrophotographic apparatus to paper or to an intermediate transfer belt.